

TECHNICAL DATA SHEET

Issued: February 2017	Product	RADIPOL® A45DK02
	Product code	P66F013
	Colour	NATURAL
	References	N° CAS. 32131-17-2

Description	Polyamide 66, Standard viscosity, Dry, Bright, Heat stabilized
--------------------	--

Typical application	Base polymer for industrial yarn and compounding
----------------------------	--

Material handling	The material is supplied as granulate, packed in 500 or 1000 kg tight sealed containers. Store away from the direct rays of the sun in rooms provided with a proper ventilation. The packages must be kept closed until utilization. For the storing in silo use stainless steel or aluminum silos. Packaging materials: multilayer cardboard octabins with PE/Al/PET liner with barrier effect.
--------------------------	--

Recycling	The product can be reused after grinding and extrusion.
------------------	---

Specification and regulation	For safety instruction please refer to Material Safety Data Sheet.
-------------------------------------	--

Adequacy declarations	Product complies the Regulation: - European Directive 2011/65/EC (and successive updated and integrations) referred to the "restriction of the use of certain hazardous substances in electrical and electronic equipment". Important: the above mentioned information relates only to the materials as delivered in their original packaging. It's not applicable to the product modified with or without additional of further additives.
------------------------------	---

	Properties	Method	Unit	Value	Test conditions
Properties (1) (Typical Values)	Physical Properties				
	Density	ISO1183	Kg/dm ³	1,14	
	Relative Viscosity	Internal Method	-	2,65	Solvent: sulphuric acid 95.7% Polyamide concentration:0.01 g/ml
	Chip Size	-	mm	2,0x2.5x3,0	
	Granulometry	Internal Method	g/100 chips	1,9	
	Mechanical Properties				
	Tensile modulus	ISO 527-2/1A	MPa	3100	DAM; vel. test 1mm/min
	Yield stress	ISO 527-2/1A	MPa	80	DAM; vel. test 5mm/min
	Yield strain	ISO 527-2/1A	%	4,4	DAM; vel. test 5mm/min
	Nominal strain at break	ISO 527-2/1A	%	40	DAM; vel. test 50mm/min
	Flexural modulus	ISO 178/1A	MPa	2650	DAM; vel. test 2mm/min
	Flexural strength	ISO 178/1A	MPa	110	DAM; vel. test 2mm/min
	Charpy impact strength	ISO 179 eU	KJ/m ²	NB	DAM; T=23°C
	Charpy notched impact strength	ISO 179 eA	KJ/m ²	5,0	DAM; T=23°C
Thermal Properties					
Melting temperature	ISO 11357-1-3	°C	260	Scanning rate 10°C/min	

Notes: (1) test specimens were obtained according ISO 1874-2.
DAM = dry as moulded state