

PRODUCT INFORMATION

RADILON S CP300K 100 NT

PRELIMINARY

DESCRIPTION

PA6 30% mineral filled injection moulding grade. Heat stabilized. Natural colour.

Suitable for parts requiring good dimensional stability and mechanical properties, reduced shrinkage and low warpage.

ISO 1043: PA6 MX30

THE CHARACTERISTICS SHOWN HERE MUST BE CONSIDERED PRELIMINARY AND INDICATIVE FOR A PRODUCT AT DEVELOPMENTAL STAGE

REGIONAL AVAILABILITY: North America, Europe, Asia Pacific, South and Central America, Near East/Africa

MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Injection Molding Processing Parameters

Melt Temperature
240 - 280°C

Mold Temperature
80 - 90°C

Injection Speed
medium-high

PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet
ROHS compliant 2011/65/UE and following amendments

TECHNICAL DATA SHEET

RADILON S CP300K 100 NT

PROPERTY	STANDARD	UNIT	VALUE	
			DAM*	Cond**
PHYSICAL PROPERTIES				
Density		kg/m ³	1350	
Moulding shrinkage - Parallel / Normal	280 / 80 / 60 ^[1]	%	0.9 / 0.9	
Water Absorption, immersion at 23°C	2mm	%	7.3	
Moisture Absorption 23°C - 50%RH	2mm	%	2.1	
MECHANICAL PROPERTIES				
Tensile Modulus	1mm/min	MPa	5000	2350
Stress at Yield	50mm/min	MPa	80	55
Strain at Break	5mm/min	%	20	35
Flexural Modulus	2mm/min	MPa	4500	
Flexural Strength	2mm/min	MPa	130	
Charpy Notched Impact Strength	+23°C	kJ/m ²	6	6.5
THERMAL PROPERTIES				
Melting Temperature	10°C/min	°C	220	
Heat Deflection Temperature	1.80 MPa	°C	90	
Heat Deflection Temperature	0.45 MPa	°C	190	
Vicat Softening Temperature	50°C/h 50N	°C	205	
FLAMMABILITY PROPERTIES				
Flammability	0.8mm	UL 94	class	HB
Glow Wire Flammability Index	2mm	IEC 60695-2-1/2	°C	700
Automotive Interior Flammability	3mm	ISO 3795	mm/min	0
ELECTRICAL PROPERTIES				
Volume Resistivity	500V	IEC 60093	Ohm*m	1E13 1E11
Surface Resistivity	500V	IEC 60093	Ohm	1E12 1E10

*: DAM = Dry As Moulded state according to ISO 16396-2 **: Cond = Conditioned state similar to ISO 1110 1: Melt Temperature [°C] / Mold Temperature [°C] / Cavity Pressure [MPa]