

# HERAFLEX E 6521 1000 NAT

*Material code**Colour code*

## DESCRIPTION

TPC-ET Thermoplastic Elastomer. Medium-high Modulus, Nominal Shore D/15s 57. Natural colour

ISO 1043 : TPC-ET

## MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.05%. Typical conditions with a desiccant drier: temperature 110 ° C, dew point -30 ° C or below, time 2-4 h or more.

Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

### Processing Parameters

Melt Temperature:	Mold Temperature:	Injection Speed:
230 ÷ 240 °C	30 ÷ 50 °C	Medium

## PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet

RoHS compliant 2002/95/CE and following amendments

## Technical data sheet

# HERAFLEX E 6521 1000 NAT

Material code      Colour code

PROPERTY		STANDARD	UNIT	VALUE
<b>Physical Properties</b>				
Density		ISO 1183	Kg/m <sup>3</sup>	1230
Melt Flow Rate	230°C/ 2.16kg	ISO 1133	g/10'	23
Shore D Hardness	3s	ISO 868	-	65
Shore D Hardness	15s	ISO 868	-	57
Abrasion resistance		ASTM D 1004	mm <sup>3</sup>	20
Tear Strength		DIN 53516	N/mm	241
<b>Mechanical Properties</b>				
Tensile Modulus	1mm/min	ISO 527-2/1A	MPa	390
Stress at 10% Strain	50mm/min	ISO 527-2/1A	MPa	19
Stress at 100% Strain	50mm/min	ISO 527-2/1A	MPa	22
Stress at Yield	50mm/min	ISO 527-2/1A	MPa	25
Yield Strain	50mm/min	ISO 527-2/1A	%	25
Stress at Break	50mm/min	ISO 527-2/1A	MPa	38
Nominal Strain at Break	50mm/min	ISO 527-2/1A	%	600
Flexural Modulus	2mm/min	ISO 178	MPa	370
Flexural Strength	2mm/min	ISO 178	MPa	20
Charpy Notched Impact Strength	+23°C	ISO 179/1 eA	KJ/m <sup>2</sup>	70
<b>Thermal Properties</b>				
Melting Temperature	10°C/min	ISO 11357-1-3	°C	212
Heat Deflection Temperature	1.8 MPa	ISO 75/2 A f	°C	60
Heat Deflection Temperature	0.45 MPa	ISO 75/2 B f	°C	110
Vicat Softening Temperature	50°C/h	ISO 306/B50 50N	°C	195
<b>Electrical Properties</b>				
Volume resistivity	500V	IEC 60093	ohm · m	1E+13
Surface resistivity	500V	IEC 60093	ohm	1E+12

\*Melt Temp [°C] / Mold Temp [°C] / Cavity press [MPa]

Issued: 02/12/2013

[www.radicigroup.com/plastics](http://www.radicigroup.com/plastics) - [info.plastics@radicigroup.com](mailto:info.plastics@radicigroup.com)

The information provided in this documentation corresponds to our knowledge on the subject at the date of its publication. This information may be subject to revision as new knowledge and experience become available. The data provided reflects the average values of the properties measured over an adequate number of different production cycles and relates only to the designated material; this data may not be valid for such material used in combination with any other materials or additives or in any process, unless expressly indicated otherwise. The data provided should not be used to establish specification limits nor used alone as the basis of design; it is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of a specific material for your particular purposes. Since Radici Plastics cannot anticipate all variations in actual end-use conditions Radici Plastics makes no warranties and assumes no liability in connection with any use of this information. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent rights.