

Technical Data Sheet

Preliminary data

nr. Tec. Data Sheet: RCH-18	Product RADIPOL® DD95
Issued: 03/04/2015	Product code P66F033
	Colour NATURAL
	References N° CAS. 26098-55-5

Description	Polyamide 6.12 dry, high viscosity
--------------------	------------------------------------

Typical application	Base polymer for monofilament
----------------------------	-------------------------------

Material handling	The material is supplied as granulate, dry, packed in 500 or 900 kg tight sealed containers. Store away from the direct rays of the sun in rooms provided with a proper ventilation. The packages must be kept closed until utilization. For the storing in silo use stainless steel or aluminum silos. Packaging materials: multilayer cardboard octabins, polythene-aluminum bags with barrier effect.
--------------------------	--

Recycling	The product can be reused after grinding and extrusion.
------------------	---

Specification and regulation	For safety instruction please refer to Material Safety Data Sheet.
-------------------------------------	--

Adequacy declarations	<p>The product complies:</p> <ul style="list-style-type: none"> - European Regulation 10/2011 (and to successive updated and integrations) - Ministerial Decree 174/2004 (and to successive updated and integrations) relating to the use of materials that come into contact with drinking water. - European Directive 2011/65/EC (and successive updated and integrations) referred to the "restriction of the use of certain hazardous substances in electrical and electronic equipment". <p>Important: the above mentioned information relates only to the materials as delivered in their original packaging. It's not applicable to the product modified with or without addition of further additives.</p>
------------------------------	---

Properties (1)	Properties	Method	Units	Value	Test conditions
	Physical Properties				
	Density	ISO1183	Kg/dm ³	1,06	
	Relative Viscosity	Int. met.	-	3.9	Solvent: sulphuric acid 96%
	Water absorption	ISO 62	%	2.7	23°C, saturation
				1.0	23°C, 50% r. h.
Mechanical Properties					
	Tensile modulus	ISO 527-2/1A	MPa	2200	DAM; vel. test 1mm/min
	Yield stress	ISO 527-2/1A	MPa	60	DAM; vel. test 5mm/min
	Yield strain	ISO 527-2/1A	%	4.2	DAM; vel. test 5mm/min
	Nominal strain at break	ISO 527-2/1A	%	45	DAM; vel. test 50mm/min
	Flexural modulus	ISO 178/1A	MPa	2200	DAM; vel. test 2mm/min
	Flexural strength	ISO 178/1A	MPa	81	DAM; vel. test 2mm/min
	Charpy impact strength	ISO 179 eU	KJ/m ²	NB	DAM; T=23°C
	Charpy notched impact strength	ISO 179 eA	KJ/m ²	6	DAM; T=23°C
Thermal Properties					
	Melting temperature	ISO 11357-1-3	°C	215	Scanning rate 10°C/min


Notes: (1) test specimens were obtained according ISO 1874-2.
DAM = dry as moulded state

Technical Data Sheet

Preliminary data

nr. Tec. Data Sheet:
RCH-18
Issued:
03/04/2015

Product	RADIPOL® DD95
Product code	P66F033
Colour	NATURAL
References	N° CAS. 26098-55-5



Declarations	The above mentioned technical data are simply indicative for users and they are given without any guarantee. They are not to be considered as specifications. Any modification/additivation of the material after the supplying can involve variation of the values or the technical characteristics. The values are calculated on injection moulded samples. Radici Chimica S.p.A. makes no warranties and assumes no liability in connections with any use of this information.
---------------------	---