

TECHNICAL DATA SHEET



| Issued: | |
|---------------|--|
| December 2016 | |

| Product | RADIPOL® A4502 |
|--------------|--------------------|
| Product code | P66F005 |
| Colour | NATURAL |
| References | N° CAS. 32131-17-2 |

| References | | | | | |
|--|--|--|--|--|--|
| | | | | | |
| Polyamide 6,6 standard viscosity | | | | | |
| | | | | | |
| Base polymer for melt spinning and compounding | | | | | |
| | | | | | |
| The material is supplied as granulate, packed in 1000 kg tight sealed containers. Store away from the direct rays of the sun in rooms provided with a proper ventilation. The packages must be kept closed until utilization. For the storing in silo use stainless steel or aluminum silos. Packaging materials: multilayer cardboard octabins with PE liner. | | | | | |
| | | | | | |
| The product can be reused after grinding and extrusion. | | | | | |
| | | | | | |
| For safety instruction please refer to Material Safety Data Sheet. | | | | | |
| | | | | | |
| Product complies the Regulation: | | | | | |
| European Directive 2011/65/EC (and successive updated and integrations) referred to the "restriction of the use of certain hazardous substances in electrical and electronic equipment". | | | | | |
| Important: the above mentioned information relates only to the materials as delivered in their original packaging. It's not applicable to the product modified with or without additional of further additives. | | | | | |
| | | | | | |

| | Properties | Method | Unit | Value | Test conditions | |
|------------------------------------|-----------------------------------|-----------------|--------------------|-------------|---|--|
| Properties (1) (Typical Values) | Physical Properties | | | | | |
| | Density | ISO1183 | Kg/dm ³ | 1,14 | | |
| | Relative Viscosity | Internal Method | - | 2,55 | Solvent: sulphuric acid 95.7% Polyamide concentration:0.01 g/ml | |
| | Chip Size | - | mm | 2,0x2,5x3,0 | | |
| | Granulometry | Internal Method | g/100 chips | 1,9 | | |
| | Yellow Index | Internal Method | - | - 6 max | | |
| | Thermal Properties | | | | | |
| | Melting temperature | ISO 11357-1-3 | °C | 260 | Scanning rate 10°C/min | |
| Notes: (1) test specime | ens were obtained according ISO 1 | 874-2. | • | | | |