

PRODUCT INFORMATION

RADILON MIXLOY S CPA100K 100 NT

PRELIMINARY

DESCRIPTION

PA6/ABS blend, 10% mineral filled injection moulding grade. Heat stabilized. Natural colour.

Suitable for parts requiring good dimensional stability and low warpage. Improved impact resistance and good property retention after moisture absorption.

ISO 1043: (PA6+ABS)-T MX10

Formerly known as LX19123.

THE CHARACTERISTICS SHOWN HERE MUST BE CONSIDERED PRELIMINARY AND INDICATIVE FOR A PRODUCT AT DEVELOPMENTAL STAGE

REGIONAL AVAILABILITY: North America, Europe, Asia Pacific, South and Central America, Near East/Africa

MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more. Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

Injection Molding Processing Parameters

Melt Temperature
240 - 260°C

Mold Temperature
40 - 60°C

Injection Speed
medium

PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet
ROHS compliant 2011/65/EU and following amendments

TECHNICAL DATA SHEET

RADILON MIXLOY S CPA100K 100 NT

PROPERTY	STANDARD	UNIT	VALUE	
			DAM*	Cond**
PHYSICAL PROPERTIES				
Density	ISO 1183	kg/m ³	1140	
Water Absorption, immersion at 23°C	2mm ISO 62	%	5.5	
Moisture Absorption 23°C - 50%RH	2mm ISO 62	%	1.7	
MECHANICAL PROPERTIES				
Tensile Modulus	1mm/min ISO 527-2/1A	MPa	2800	1300
Stress at Yield	50mm/min ISO 527-2/1A	MPa	55	35
Yield Strain	ISO 527-2/1A	%	3	15
Nominal Strain at Break	50mm/min ISO 527-2/1A	%	45	100
Flexural Modulus	2mm/min ISO 178	MPa	2900	1300
Flexural Strength	2mm/min ISO 178	MPa	90	45
Charpy Impact Strength	+23°C ISO 179/1eU	kJ/m ²	N	N
Charpy Notched Impact Strength	+23°C ISO 179/1eA	kJ/m ²	10	18
Charpy Notched Impact Strength	-30°C ISO 179/1eA	kJ/m ²	9	
THERMAL PROPERTIES				
Melting Temperature	10°C/min ISO 11357-1/-3	°C	222	
Vicat Softening Temperature	50°C/h 50N ISO 306	°C	135	

*: DAM = Dry As Moulded state according to ISO 16396-2 **: Cond = Conditioned state similar to ISO 1110