

# RADILON A RV150W 333 NER 6663

Material code

Colour code

PROVISIONAL

## DESCRIPTION

PA66 15% glass fiber reinforced injection moulding grade. Heat stabilized. Black colour.

Suitable for parts requiring improved stiffness and good heat ageing properties retention..

ISO 1043 : PA66-T GF15

## MATERIAL HANDLING AND PROCESSING

The material is delivered in moisture-proof packaging ready for processing. Maximum recommended water content for best processing is 0.15%. Typical conditions with a desiccant drier: temperature 80 ° C, dew point -20 ° C or below, time 2-4 h or more.

Special care must be taken to avoid moisture absorption and contamination with other polymers when adding regrind material. Colour variation and mechanical properties reduction may occur and should always be carefully monitored.

### Processing Parameters

Melt Temperature:	Mold Temperature:	Injection Speed:
280 ÷ 300 °C	80 ÷ 100 °C	Medium

## PRODUCT SAFETY AND APPROVALS

For safety instruction please refer to Material Safety Data Sheet

RoHS compliant 2011/65/UE and following amendments

## Technical data sheet

PROVISIONAL

# RADILON A RV150W 333 NER 6663

Material code Colour code

PROPERTY	STANDARD	UNIT	VALUE	
			DAM*	Cond**
<b>Physical Properties</b>				
Density	ISO 1183	Kg/m <sup>3</sup>	1230	
Moulding shrinkage – Parallel / Normal	300/90/60***	ISO 294-4	%	0,4 / 0,9
Moisture absorption 23°C – 50%RH	2mm thk	ISO 62	%	2.3
Water absorption, immersion at 23°C	2mm thk	ISO 62	%	7.9
<b>Mechanical Properties</b>				
Tensile Modulus	1mm/min	ISO 527-2/1A	MPa	5800 3900
Stress at Break	5mm/min	ISO 527-2/1A	MPa	115 85
Strain at Break	5mm/min	ISO 527-2/1A	%	2,5 4
Flexural Modulus	2mm/min	ISO 178	MPa	5400
Flexural Strength	2mm/min	ISO 178	MPa	165
Charpy Impact Strength	+23°C	ISO 179/1 eU	KJ/m <sup>2</sup>	30 70
Charpy Notched Impact Strength	+23°C	ISO 179/1 eA	KJ/m <sup>2</sup>	6 8
Charpy Notched Impact Strength	-30°C	ISO 179/1 eA	KJ/m <sup>2</sup>	5,5 6
<b>Thermal Properties</b>				
Melting Temperature	10°C/min	ISO 11357-1-3	°C	260
Heat Deflection Temperature	1.8 MPa	ISO 75/2 A f	°C	215
Heat Deflection Temperature	0.45 MPa	ISO 75/2 B f	°C	240
Vicat Softening Temperature	50°C/h	ISO 306/B50 50N	°C	245
<b>Flammability Properties</b>				
Flammability	0.8mm	UL 94	class	HB
Glow Wire Flammability Index	2mm	IEC 60695-2-1/2	°C/mm	650
Automotive interior flammability	Burn rate	FMVSS302	mm/min	0
<b>Electrical Properties</b>				
Volume resistivity	500V	IEC 60093	ohm · m	1 E+13 1 E+11
Surface resistivity	500V	IEC 60093	ohm	1 E+12 1 E+10

The characteristics shown here must be considered purely provisional and indicative for a product at developmental stage.

\*DAM = Dry As Moulded state \*\*Cond = Conditioned state similar to ISO 1110 \*\*\*Melt Temp [°C] / Mold Temp [°C] / Cavity press [MPa]